



## UMI Plasterboard Standards compared with ASTM C1396 and DIN EN 520 Standard Limits

SPECIFICATIONS

### 1- DIMENSIONS

The Specimens	UMI Specifications Tolerances (mm)	ASTM C1396 Specifications Tolerances (mm)	DIN EN 520 Specifications Tolerances (mm)
<b>Thickness (mm)</b> 9.5 , 12.5 , 15 , 16 , 18	± 0.3	± 0.4	± 0.5
<b>Length</b> (1800 mm – 4000 mm)	0 to - 4	0 to - 6	0 to - 5
<b>Width</b> (1200 mm , 1220 mm)	0 to - 3	0 to - 3	0 to - 4
<b>Squareness (mm)</b>	≤ 2	≤ 3	≤ 2.5

### 2- FLEXURAL STRENGTH

The Specimens thickness	UMI Specifications ( N )		ASTM C1396 Specifications ( N )		DIN EN 520 Specifications ( N )	
	L	T	L	T	L	T
<b>9.5 mm</b>	≥ 485	≥ 175	≥ 356	≥ 133	≥ 400	≥ 125
<b>12.5 mm</b>	≥ 625	≥ 250	≥ 489	≥ 178	≥ 550	≥ 210
<b>15 mm</b>	≥ 720	≥ 315	≥ 667	≥ 222	≥ 650	≥ 225
<b>16 mm</b>	≥ 735	≥ 335	≥ 667	≥ 222	≥ 688	≥ 256
<b>18 mm</b>	≥ 845	≥ 470	≥ 756	≥ 267	≥ 774	≥ 288

### 3- HARDNESS

The Specimens	UMI Specifications ( N )	ASTM C1396 Specifications ( N )	DIN EN 520 Specifications ( N )
<b>CORE</b>	≥ 80.1	≥ 67	Not Specified
<b>END</b>	≥ 75.65	≥ 67	Not Specified
<b>EDGE</b>	≥ 75.65	≥ 67	Not Specified

### 4- NAIL PULL

The Specimens thickness	UMI Specifications ( N )	ASTM C1396 Specifications ( N )	DIN EN 520 Specifications ( N )
<b>9.5 mm</b>	275.6	267	Not Specified
<b>12.5 mm</b>	369.4	356	Not Specified
<b>15 mm</b>	415	400	Not Specified
<b>16 mm</b>	415	400	Not Specified
<b>18 mm</b>	460	445	Not Specified

\* The test results and pertinent information are for UMI Plasterboards of the types: - Regular , Fire Resistant , Moisture Resistant , Fire & Moisture Resistant .

ENG.

**AHMED BADAUY**

QA/QC Manager



**Head Office:**  
P.O.Box 127398 Jeddah 21352  
T. +966 2 691 3497,  
F. +966 2 682 3651,  
E-mail: jeddahsales@ugc.com.sa

**Plant Management**  
Yanbu, P.O. Box: 31491,  
T. +966 4 396 8777,  
F. +966 4 396 2666,  
E-mail: yanbusales@ugc.com.sa

**إدارة المصنع:**  
ينبع، ص.ب. ٣١٤٩١،  
هاتف: ٨٧٧٧ ٣٩٦ ٩٦٦ +  
فاكس: ٢٦٦٦ ٣٩٦ ٩٦٦ +

**المركز الرئيسي**  
ص.ب ١٢٧٣٩٨ جدة ٢١٣٥٢  
هاتف: ٣٤٩٧ ٦٩١ ٩٦٦ +  
فاكس: ٣٦٨٢ ٦٨٢ ٩٦٦ +