





المتحدة للصناعات التعدينية United Mining Industries

UMI (GKF) BOARDS FIRE RATING TIME

- THESE ARE THE UMI BOARDS WHICH HAVE FIBER GLASS INCORPORATED IN PLASTER CORE THUS ACHIEVING A GREATER FIRE RESISTANCE.
- THE BOARDS ARE MANUFACTURED ACCORDING TO EN 520 – 2004 SPECIFICATION AND CONFORMED TO SASO (ASTM C1396/C1396 M).
- FIRE REACTION CLASS: DIN 4102 PART 1 ,CLASS A2.
- FIRE RATING IS 1.5 H ACCORDING TO TEST PROCEDURE UL 263 WHICH IS IDENTICAL AND SAME AS ASTM E119.



Thickness : 12.5 mm

- Single stud work partition - Single UMI Gypsum board facing	Max Time (min.)	Max Temp. (C °)	- Single stud work partition - Double UMI Gypsum board facing	Max Time (min.)	Max Temp. (C °)
	53	1687.7		90	1806.9



Thickness : 15 mm

- Single stud work partition - Single UMI Gypsum board facing	Max Time (min.)	Max Temp. (C °)	- Single stud work partition - Double UMI Gypsum board facing	Max Time (min.)	Max Temp. (C °)
	67	1738.6		112	1854.5

Thickness : 16 mm

- Single stud work partition - Single UMI Gypsum board facing	Max Time (min.)	Max Temp. (C °)	- Single stud work partition - Double UMI Gypsum board facing	Max Time (min.)	Max Temp. (C °)
	76	1766.1		120	1879.4

Thickness : 18 mm

- Single stud work partition - Single UMI Gypsum board facing	Max Time (min.)	Max Temp. (C °)	- Single stud work partition - Double UMI Gypsum board facing	Max Time (min.)	Max Temp. (C °)
	90	1780.7		148	1941.3

ENG.
AHMED BADAWY
QA/QC Manager



Head Office:
P.O.Box 127398 Jeddah 21352
T. +966 2 691 3497,
F. +966 2 682 3651,
E-mail: jeddahsales@ugc.com.sa

Plant Management
Yanbu, P.O. Box: 31491,
T. +966 4 396 8777,
F. +966 4 396 2666,
E-mail: yanbusales@ugc.com.sa

إدارة المصنع:
ينبع، ص.ب. ٣١٤٩١،
هاتف: ٨٧٧٧ ٣٩٦ ٤٩٦٦
فاكس: ٢٦٨٢ ٣٩٦ ٤٩٦٦

المركز الرئيسي
ص.ب. ١٢٧٣٩٨ جدة ٢١٣٥٢
هاتف: ٣٤٩٧ ٦٩١ ٩٦٦٦
فاكس: ٣٦٨٢ ٦٩١ ٩٦٦٦